

Orbital-assisted metal-insulator transition in VO₂

M. W. Haverkort,¹ Z. Hu,¹ A. Tanaka,² W. Reichelt,³ S. V. Streltsov,⁴ M. A. Korotin,⁴ V. I. Anisimov,⁴ H. H. Hsieh,⁵ H.-J. Lin,⁶ C. T. Chen,⁶ D. I. Khomskii,¹ and L. H. Tjeng¹

¹*II. Physikalisches Institut, Universität zu Köln, Zùlpicher Str. 77, D-50937 Köln, Germany*

²*Department of Quantum Matter, ADSM, Hiroshima University, Higashi-Hiroshima 739-8530, Japan*

³*Institut für Anorganische Chemie, Technische Universität Dresden, Mommsenstr. 13, D-01069, Dresden, Germany*

⁴*Institute of Metal Physics, S. Kovalevskoy 18, 620219 Ekaterinburg GSP-170, Russia*

⁵*Chung Cheng Institute of Technology, National Defense University, Taoyuan 335, Taiwan*

⁶*National Synchrotron Radiation Research Center, 101 Hsin-Ann Road, Hsinchu 30077, Taiwan*

(Dated: February 2, 2008)

We found direct experimental evidence for an orbital switching in the V 3d states across the metal-insulator transition in VO₂. We have used soft-x-ray absorption spectroscopy at the V *L*_{2,3} edges as a sensitive local probe, and have determined quantitatively the orbital polarizations. These results strongly suggest that, in going from the metallic to the insulating state, the orbital occupation changes in a manner that charge fluctuations and effective band widths are reduced, that the system becomes more 1-dimensional and more susceptible to a Peierls-like transition, and that the required massive orbital switching can only be made if the system is close to a Mott insulating regime.

PACS numbers: 71.10.-w, 71.30.+h, 71.70.-d, 78.70.Dm

The problem of metal-insulator transitions (MIT) in transition metal compounds attracts considerable attention already for a long time. Among the best studied of such systems are the V oxides, especially V₂O₃ and VO₂ [1, 2]. The long-standing problem in these systems is the relative role of electron-lattice interactions and corresponding structural distortions versus electron correlations. This problem is especially acute for the MIT in VO₂, which was described either as predominantly a Peierls transition [3] or as a Mott-Hubbard transition [4].

An intriguing aspect that has largely been neglected in the discussions about MIT in TM oxides is the possible role of magnetic correlations and especially the orbital structure of constituent TM ions [5]. Very recently, a theoretical model for spinels such as MgTi₂O₄ and CuIr₂S₄ has been proposed in which a specific orbital occupation effectively leads to the formation of one-dimensional bands, making the systems, in a natural manner, susceptible to a Peierls-like MIT [6].

The crystal and electronic structure of VO₂ is in this respect more intricate. The MIT in VO₂ is a structural transition from the high-temperature rutile (R) structure to a monoclinic (M₁) structure, in which there appears simultaneous *dimerization* in each V chain along the *c*-axis and a *twisting* of V-V pairs due to an antiferroelectric shift of neighboring V atoms towards the apex oxygens (lying at the axis perpendicular to the crystal *c*-axis), see Fig. 1. As argued already long ago by Goodenough [7], one should discriminate between two types of orbitals and corresponding bands: *d*_{||}-orbitals/bands, formed by the *t*_{2g}-orbitals with strong direct overlap with the neighboring V in the chains, and *π**-orbitals/bands, made of the two other *t*_{2g}-orbitals. In the R-phase, the *d*_{||} band overlaps with the *π**-band, resulting in an orbitally isotropic metallic state, see Fig. 2. The twisting in the M₁-phase




FIG. 1: Crystal structure of VO₂ in the metallic rutile (R) phase and in the insulating monoclinic (M₁) phase. The arrows show the direction of the displacements of the V ions in the M₁-phase. The *a*, *b* and *c*-axes are defined with respect to the rutile structure.

increases the V - apex O hybridization and moves the *π** band up, so that only the *d*_{||} band is occupied. The later one then becomes split by the dimerization, leading to the insulating state.

Many theoretical *ab-initio* studies were performed to test the Goodenough picture. LDA calculations indicated indeed that the *d*_{||} band becomes more occupied in the M₁-phase [3, 8], but they failed to reproduce the insulating state. An L(S)DA+U approach predicted even more dramatic changes in the orbital occupations, but unfortunately it did not give the metallic solution for the R-phase [9, 10]. A change in the orbital occupation was




FIG. 2: Top panel: schematic electronic structure of VO₂ according to Goodenough [7]; bottom panel: definitions of the relevant V 3d t_{2g} orbitals used in this work, drawn in the (110) plane spanned by the a , b and c -axes of Fig. 1. Site 1 and 2 are related by a 90° rotation around the c -axis.

also obtained in the exact diagonalization study for a three-band Hubbard model using finite size clusters [11]. Very recently, various LDA+DMFT methods have been applied to explain the MIT, and also here the orbital occupations are an important issue [10, 12, 13]. In view of the fact that the orbital occupation and changes thereof are central to the MIT theories for VO₂, it is quite surprising that an experimental proof of it is lacking, an aspect which is also relevant for other materials [14, 15].

In this paper we give a direct experimental evidence of this orbital redistribution at the MIT in VO₂. We present a polarization-dependent x-ray absorption spectroscopy (XAS) study on VO₂ single crystals at the V $L_{2,3}$ ($2p \rightarrow 3d$) edges. Here we make use of the fact that the Coulomb interaction of the $2p$ core hole with the $3d$ electrons is much larger than the $3d$ t_{2g} band width, so that the absorption process is strongly excitonic and therefore well understood in terms of atomic-like transitions to multiplet split final states subject to dipole selection rules. This makes the technique an extremely sensitive local probe [16, 17, 18], ideal to study the orbital character [5, 19] of the ground or initial state. For our experiment on VO₂, we redefine the orbitals in terms of σ , π , or δ with respect to the V chain as shown in Fig. 2. The σ orbital is then equivalent to the $d_{||}$, and the π and δ to the π^* . The transition probability will strongly depend on which of the σ , π , or δ orbitals are occupied and on how the polarization vector $\vec{E}$ of the light is oriented. Our measurements reveal a dramatic switching of the orbital occupation across the MIT, even more than in V₂O₃ [5], indicating the crucial role of the orbitals and lattice in the correlated motion of the electrons.

Single crystals of VO₂ with $T_{MIT} = 67^\circ\text{C}$ have been grown by the vapor transport method [20]. The XAS measurements were performed at the Dragon beamline of the NSRRC in Taiwan. The spectra were recorded us-




FIG. 3: Experimental V $L_{2,3}$ XAS spectra of VO₂ in the insulating M₁-phase (top panel, T=30°C) and metallic R-phase (bottom panel, T=100°C), taken with the light polarization $\vec{E} \parallel c$ (solid lines) and $\vec{E} \perp c$ (dashed lines). The metal-insulator transition temperature is 67 °C.

ing the total electron yield method in a chamber with a base pressure of 3×10^{-10} mbar. Clean sample areas were obtained by cleaving the crystals *in-situ*. The photon energy resolution at the V $L_{2,3}$ edges ($h\nu \approx 510 - 530$ eV) was set at 0.15 eV, and the degree of linear polarization was $\approx 98\%$. The VO₂ single crystal was mounted with the c -axis perpendicular to the Poynting vector of the light. By rotating the sample around this Poynting vector, the polarization of the electric field vector can be varied continuously from $\vec{E} \parallel c$ to $\vec{E} \perp c$. This measurement geometry allows for an optical path of the incoming beam which is independent of the polarization, guaranteeing a reliable comparison of the spectral line shapes as a function of polarization.

Fig. 3 shows the V $L_{2,3}$ XAS spectra of VO₂ taken in the insulating M₁-phase (top panel), and in the metallic R-phase (bottom panel). The general lineshape of the spectra is similar to that in earlier works, each of which only reports spectra for one particular polarization [21, 22]. In our work, we have measured for each phase the spectra with two different light polarizations, namely $\vec{E} \parallel c$ (solid lines) and $\vec{E} \perp c$ (dashed lines). We observe a clear polarization dependence for the insulating phase.




FIG. 4: Theoretical simulations for the polarization dependent V $L_{2,3}$ XAS spectra. Left panel: best fit to the experimental spectra, using orbital occupations as indicated in Table I. Right panel: simulations for the V $3d^1$ ion assuming a pure σ , π , or δ orbital occupation. Top part of the panels: simulations for the insulating M_1 -phase. Bottom part of the panels: *idem* for the metallic R-phase.

By contrast, the polarization dependence is quite weak for the metallic phase. Fig. 3 shows for each phase also the dichroic spectrum, i.e. the difference between the spectra taken with the two polarizations. One now can see that the dichroic spectrum of the insulating phase has not only a larger amplitude, but also a very different lineshape than that of the metallic phase.

To extract information concerning the orbital occupation from the V $L_{2,3}$ XAS spectra, we have performed simulations of the atomic-like $2p^6 3d^1 \rightarrow 2p^5 3d^2$ transitions using the well-proven configuration interaction cluster model [16, 17, 18]. The method uses a VO_6 cluster which includes the full atomic multiplet theory and the local effects of the solid. It accounts for the intra-atomic $3d$ - $3d$ and $2p$ - $3d$ Coulomb interactions, the atomic $2p$ and $3d$ spin-orbit couplings, the O $2p$ - V $3d$ hybridization, and local crystal field parameters. Parameters for the multipole part of the Coulomb interactions were given by the Hartree-Fock values [16], while the monopole parts (U_{dd} , U_{pd}) as well as the O $2p$ - V $3d$ charge transfer energy were determined from photoemission experiments [23]. The one-electron parameters such as the O $2p$ - V $3d$ and O $2p$ - O $2p$ transfer integrals as well as the local crystal fields were extracted from the LDA band structure results [9] for the crystal structure corresponding to each of the two phases of VO_2 . The simulations have been carried out using the XTLS 8.0 program [11, 16, 24].

Fig. 4 shows the results of our theoretical simulations of the spectra. In the top part of the right panel we have simulated the insulating M_1 -phase spectra for the following three scenarios: the V $3d^1$ ion is set either in the pure σ , π , or δ -orbital symmetry. One can clearly observe that the different orbital symmetries will lead to very differ-

	M ₁ -phase				R-phase			
	fit to exp. sym.	n_{3d}	<i>ab-initio</i> LDA	LSDA+U	fit to exp. sym.	n_{3d}	<i>ab-initio</i> LDA	LSDA+U
σ	0.81	0.86	0.64	0.89	0.33	0.41	0.43	0.20
π	0.10	0.21	0.39	0.23	0.16	0.25	0.35	0.24
δ	0.09	0.17	0.41	0.25	0.51	0.58	0.67	0.97
e_{g1}	0.00	0.27	0.46	0.40	0.00	0.27	0.47	0.42
e_{g2}	0.00	0.32	0.53	0.51	0.00	0.27	0.48	0.48
tot.	1.00	1.83	2.43	2.48	1.00	1.78	2.40	2.31

TABLE I: Symmetry and orbital occupation of the $3d$ shell of VO_2 in the M_1 - and R-phase.

ent spectra with quite different polarization dependence. One can notice that the σ -orbital scenario resembles the experimental spectra the most, especially when one focuses on the most excitonic part of the spectrum, namely between 512 and 516 eV. In a simulation with the V ion in the ground state that belongs to the true local symmetry of the M_1 -phase, we find even a better fit to the experimental data as shown in the left panel. The corresponding orbital symmetry, as listed in the left column of Table I, has indeed overwhelmingly the σ character (0.81), and only very little π (0.10) and δ (0.09).

We have also simulated the spectra for the metallic R-phase, again for the three scenarios in which the V ion set to have either the pure σ , π , or δ -orbital symmetry. The bottom part of the right panel shows that each scenario results in quite different spectra and polarization dependence. We also note that each of the R-phase scenario gives spectra different from the corresponding M_1 -phase, simply because of the differences in the local electronic structure, resulting from the differ-

ent crystal structure. Important is now that none of the three scenarios of the R-phase give good agreement with the experimental spectra. Apparently, the V ion has an orbital symmetry which is very far from a pure σ , or π , or δ . We now approximate the initial state symmetry of the V ion by a linear combination of those three symmetries, and optimize the relative weights to obtain the best fit to the experiment, with the emphasis on the excitonic part. Fig. 4 (bottom left panel) shows that this state is built up of 0.33 σ , 0.16 π and 0.51 δ symmetries, see also the 5th column of Table I. It seems thus that in the metallic phase the V orbital occupation is almost isotropic.

In Table I we have also listed the $3d$ orbital occupation as found from the simulations of the experimental spectra. These numbers are not identical to the symmetry occupation numbers because of the covalency, i.e. the hybridization of the V $3d$ with the surrounding O $2p$ ligands. We now can compare our findings directly with the numbers from our LDA and LSDA+U calculations [9]. We note that our LDA band structure is quite similar to the one published earlier [3, 8], and that the occupation numbers of our LSDA+U is in close agreement with the one published very recently [10]. For the insulating M_1 -phase, we find that the orbital occupation, which is highly (σ) polarized, is well reproduced by the LSDA+U model but not so by the standard LDA, see Table I. On the other hand, for the metallic R-phase, we observe that the almost isotropic orbital occupation as experimentally determined is well reproduced by the LDA, but not so by the LSDA+U. It seems that the LDA tends to underestimate the orbital polarization, which makes the method less suitable for the insulating phase. The LSDA+U, on the other hand, tend to overestimate it, which puts this approach in disadvantage for the metallic phase. These problems are likely to be related to the fact that the LDA cannot reproduce the insulating state in the M_1 -phase, while the LSDA+U does not give the metallic state for the R-phase. Nevertheless, the general trend that the orbital occupation is more σ -polarized in the M_1 -phase is predicted correctly in both approaches.

In comparing our experimental results with the DMFT calculations, we note that in one implementation of the standard LDA+DMFT method the change in orbital polarization is too small which has been attributed to the fact that the insulating phase cannot be reproduced [10]. Very exciting is that an LDA+cluster/DMFT study [13] has been very successful in reproducing the strong change in orbital polarization, indicating the importance of the k -dependence of the self-energy correction.

The significant outcome of our experiments is that the orbital occupation changes from almost isotropic in the metallic phase to the almost completely σ -polarized in the insulating phase, in close agreement with the three band Hubbard model [11]. This very strong change leads to a dramatic modification of the intersite exchange interactions with large consequences for the effective Hub-

bard U for nearest neighbor charge fluctuations [5, 11] and effective band widths [5]. Moreover, the orbital polarization change is such that VO_2 in terms of its electronic structure is transformed from a 3-dimensional to effectively a 1-dimensional system [6]. The V ions in the chain along the c -axis are then very susceptible to a Peierls transition. In this respect, the MIT in VO_2 indeed has many features of a Peierls transition [3]. However, to get the dramatic change of the orbital occupation one also need the condition that strong electron correlations bring this narrow band system close to the Mott regime [4]. The MIT in VO_2 may therefore be labelled as an orbital assisted "collaborative" Mott-Peierls transition.

To conclude, we have found direct experimental evidence for an orbital switching in the V $3d$ states across the metal-insulator transition in VO_2 . The orbital occupation in the insulating state is such that the effective band widths are reduced and the system electronically more 1-dimensional and thus more susceptible to a Peierls-like transition.

We acknowledge the NSRRC for providing an extremely stable beam. We thank Lucie Hamdan for her skillful technical assistance, and N. Skorikov and Z. Pchelkina for discussions. The research in Köln is supported by the Deutsche Forschungsgemeinschaft (DFG) through SFB 608, and the research in Ekaterinburg by the Russian Foundation for Basic Research (RFFI) 04-02-16096 and 03-0239024, and the Netherlands Organization for Scientific Research (NWO) 047.016.005.

-
- [1] N. Tsuda, K. Nasu, A. Yanase, and K. Siratori, *Electronic Conduction in Oxides* (Springer Series in Solid-State Sciences 94, Springer Verlag, Berlin 1991)
 - [2] M. Imada, A. Fujimori, and Y. Tokura, *Rev. Mod. Phys.* **70**, 1039 (1998)
 - [3] R. M. Wentzcovitch, W. W. Schulz, and P. B. Allen, *Phys. Rev. Lett.* **72**, 3389 (1994).
 - [4] T. M. Rice, H. Launois, J. P. Pouget, *Phys. Rev. Lett.* **73**, 3042 (1994).
 - [5] J.-H. Park *et al.*, *Phys. Rev. B* **61**, 11506 (2000).
 - [6] D. I. Khomskii and T. Mizokawa, *Phys. Rev. Lett.* **94**, 156402 (2005).
 - [7] J. B. Goodenough, *J. Solid State Chem.* **3**, 490 (1971).
 - [8] V. Eyert, *Ann. Phys. (Leipzig)* **11**, 650 (2002).
 - [9] M. A. Korotin, N. A. Skorikov, and V. I. Anisimov, *Phys. Met. Metallogr.* **94**, 17 (2002), cond-mat/0301347 v1
 - [10] A. Liebsch, H. Ishida, and G. Bihlmayer, *Phys. Rev. B* **71**, 085109 (2005).
 - [11] A. Tanaka, *J. Phys. Soc. Jpn.* **73**, 152 (2004).
 - [12] M. S. Laad, L. Craco, and E. Müller-Hartmann, cond-mat/0305081;0409027.
 - [13] S. Biermann, A. Poteryaev, A. I. Lichtenstein, and A. Georges, *Phys. Rev. Lett.* **94**, 026404 (2005).
 - [14] M. P. Pasternak *et al.*, *Phys. Rev. B* **65**, 035106 (2001).
 - [15] J. Kunes *et al.*, *Phys. Rev. B* **68**, 115101 (2003).
 - [16] A. Tanaka and T. Jo, *J. Phys. Soc. Jpn.* **63**, 2788 (1994).

- [17] F. M. F. de Groot, J. Electron Spectrosc. Relat. Phenom. **67**, 529 (1994).
- [18] Theo Thole Memorial Issue, J. Electron Spectrosc. Relat. Phenom. **86**, 1 (1997).
- [19] C. T. Chen *et al.*, Phys. Rev. Lett. **68**, 2543 (1992).
- [20] W. Brückner, H. Oppermann, W. Reichelt, J. I. Terukow, F. A. Tschudnowski, and E. Wolf, *Vanadiumoxide* (Akademie-Verlag, Berlin, 1983).
- [21] M. Abbate *et al.*, Phys. Rev. B **43**, 7263 (1991).
- [22] E. Goering, O. Möller, M. L. denBoer, and S. Horn, Physica B **194**, 1217 (1994).
- [23] A. E. Bocquet *et al.*, Phys. Rev. B **53**, 1161 (1996).
- [24] Parameters for VO₆ cluster [eV]: $\Delta=2.5$, $U_{dd}=4.5$, $U_{pd}=6.1$; Slater integrals 80% of Hartree Fock values.